



# FastCat<sup>tm</sup> 30

Fast Catalyst & Cure Accelerator  
For *Mold Max<sup>tm</sup> 30* Silicone Rubber

FastCat<sup>tm</sup> 30 silicone rubber catalyst will accelerate the cure time of Mold Max<sup>tm</sup> 30 silicone rubber. Used in place of (or in combination with) Mold Max<sup>tm</sup> 30 regular Part B catalyst, FastCat<sup>tm</sup> 30 will reduce the demold time from overnight to as little as 30 minutes.

**Note:** working time is reduced in proportion to the amount of FastCat<sup>tm</sup> 30 added.

**Example:** When used alone as Part B for Mold Max<sup>tm</sup> 30 (100A:10B pbw mix ratio) instead of regular catalyst, FastCat<sup>tm</sup> 30 reduces the pot life of Mold Max<sup>tm</sup> 30 from 45 minutes to 10 minutes and the demold time from 24 hours to 1 hour. If the amount of FastCat<sup>tm</sup> 30 Part B is increased to 15% (100A:15B pbw), the pot life is reduced to 5 minutes and the demold time to 30 minutes.

### Example: FastCat<sup>tm</sup> 30 Used Instead Of Regular Part B\*

Mold Max <sup>tm</sup> 30 Part A	100 Parts	100 Parts
FastCat <sup>tm</sup> Part B	10 Parts	15 Parts
Pot Life	10 minutes	5 minutes
Demold Time	1 hour	30 minutes

\*Mix ratios are parts by weight (pbw), and accuracy must be assured by using a gram scale or triple beam balance to properly weigh the components.

**Example:** FastCat<sup>tm</sup> 30 can also be used as an accelerator in combination with regular Mold Max<sup>tm</sup> 30 Part B to reduce demold time.

### Example: FastCat<sup>tm</sup> 30 Used as Accelerator With Mold Max<sup>tm</sup> 30 Regular Part B\*

Mold Max <sup>tm</sup> 30 Part A	100 Parts	100 Parts
Mold Max <sup>tm</sup> 30 Regular Part B	8 Parts	5 Parts
FastCat <sup>tm</sup> 30	2 Parts	5 Parts
Pot Life	35 minutes	20 minutes
Demold time	4 hours	2 hours

\*Mix ratios are parts by weight (pbw), and accuracy must be assured by using a gram scale or triple beam balance to properly weigh the components.

**Mixing:** Add desired amounts of FastCat<sup>tm</sup> and/or regular Mold Max<sup>tm</sup> 30 Part B to Mold Max<sup>tm</sup> 30 Part A by weight and mix thoroughly. **Important:** Be sure to scrape the sides and bottom of the mixing container several times while mixing. Be aware of your working time with reduced pot life. **Note:** results may differ due to variables in temperature, humidity, etc.

*The Material Safety Data Sheet (MSDS) for this or any Smooth-On product should be read prior to use and is available upon request from Smooth-On. All Smooth-On products are safe to use if directions are read and followed carefully. Be careful. Use only with adequate ventilation. Contact with skin and eyes may cause irritation. Flush eyes with water for 15 minutes and seek immediate medical attention. Remove from skin with waterless hand cleaner followed by soap and water. Important:* The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe upon a patent. User shall determine the suitability of the product for the intended application and assume all risk and liability whatsoever in connection therewith.

**Toll-Free Technical Help: 800-762-0744**

**Fax: 610-252-6200**

**Or Visit Our Website: [www.smooth-on.com](http://www.smooth-on.com)**